Title

PTO/SB/05 (4-98)
Approved for use through 09/30/2000. OMB 0651-0032
Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Attorney Docket No.

### UTILITY **PATENT APPLICATION TRANSMITTAL**

(Only for new nonprovisional applications under 37 C.F.R. § 1.53(b).

First Inventor or Application Identifier

SD-8298

**Mobile Monolithic Polymer Elements for** 

Hasselbrink

Express Mail Label No.

Flow Control in Microfluidic Devices

EL177882857US

APPLICATION ELEMENTS See MPEP chapter 600 concerning utility patent application	ADDRESS TO:  Assistant Commissioner for Patents Box Patent Application	
contents.	Washington, DC 20231	
*Fee Transmittal Form (e.g., PTO/SB/17)  1. (Submit an original and duplicate for fee processing)	5. Microfiche Computer Program (Appendix)	
2. Specification [Total Pages 30 ]	Nucleotide and/or Amino Acid Sequence Submission     (if applicable, all necessary)	
(preferred arrangement set forth below) - Descriptive title of the Invention	a. Computer Readable Copy	
- Cross References to Related Applications	b. Paper Copy (identical to computer copy)	
- Statement Regarding Fed sponsored R & D	В	
- Reference to Microfiche Appendix	c. Statement verifying identity of above copies	
- Background of the Invention	ACCOMPANYING APPLICATION PARTS	
- Brief Summary of the Invention	ACCOMPANTING APPLICATION PARTS	
- Brief Description of the Drawings (if filed)	7. Assignment Papers (cover sheet & document(s))	
- Detailed Description	37 C.F.R. § 3.73(b) Statement	
<ul><li>Claim(s)</li><li>Abstract of the Disclosure</li></ul>	8. (when there is an assignee)	
- Abstract of the Disclosure	9. English Translation Document Power of Attorney	
3. Drawing(s) (35 U.S.C. 113) [Total Sheets 7]	10. Information Disclosure Statement (IDS)/PTO-1449	
4. Oath or Declaration [Total Pages ]	11. Preliminary Amendment Copies of IDS Citations	
a. Newly executed (original or copy)	Return Receipt Postcard (MPEP 503) (Should be specifically itemized)	
b. Copy from a prior application (37 C.F.R. § 1.63(d)) (for continuation/divisional with Box 16 completed)	*Small Entity Statement(s) Status still proper and desired	
j. DELETION OF INVENTOR(S) Signed statement attaced deleting inventor(s) named in the prior application,	(PTO/SB/09/12) Certified Copy of Priority Document(s) (if foreign priority is claimed)	
see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).		
	15 Other:	
*NOTE FOR ITEMS 1 & 13 IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY		
NOTE FOR ITEMS 1 & 19 IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C F R § 1 27), EXCEPT IF ONE FILED IN A PRICA APPLICATION IS RELIED UPON (37 C F R § 1 28)		
16. If a CONTINUING APPLICATION, check appropriate box, and	supply the requisite information below and in a preliminary amendment:	
Continuation Divisional Continuation-in-part (CIP)	of prior application No.:/	
Prior application information: Examiner	Group / Art Unit:	
under Box 4b, is considered a part of the disclosure of the accompar	e of the prior application, from which an oath or declaration is supplied by a continuation or divisional application and is hereby incorporated by	
reference. The incorporation can only be relied upon when a portion	has been inadvertently omitted from the submitted application parts.	
17. COORESPO	DNDENCE ADDRESS	
Customer Number or Bar Code Label (Insert   Insert   Inse		
Name   INSTITUTE		
Name 021496 ————————————————————————————————————		
Address PATENT AND	TRADEMARK OFFICE	
City State	Zip Code	
Country Telephone	Fax	
Name (Print/Type) Kurt C. Olsen Signature	Registration No. (Attorney/Agent) 29,961	



PTC/SB/17 (09-00)

Approved for use through 10/31/2002. OMB 0651-0032

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

## **FEE TRANSMITTAL** for FY 2001

Patent fees are subject to annual revision.

TOTAL	ABSOLIVIT	OF PAYME	

(\$)1840.00

Complete if Known		
Application Number	Unknown	
Filing Date	10/24/00	
First Named Inventor	Hasselbrink	
Examiner Name		
Group Art Unit		
Attorney Docket No.	SD-8298	

METHOD OF PAYMENT	FEE CALCULATION (continued)			
1. X The Commissioner is hereby authorized to charge	3. ADDITIONAL FEES			
Deposit Deposit	Large Entity Small Entity Fee Fee Fee Fee Fee Fee Description Fee Pai			
Account Number 50-0583	Code (\$) Code (\$)			
Deposit	105 130 205 65 Surcharge - late filing fee or oath			
Account SNL by KCO	127 50 227 25 Surcharge - late provisional filing fee or cover sheet			
Charge Any Additional Fee Required	139 130 139 130 Non-English specification			
— Officer 57 CFR 1.16 and 1.17	147 2,520 147 2,520 For filing a request for <i>ex parte</i> reexamination			
Applicant claims small entity status See 37 CFR 1.27	112 920* 112 920* Requesting publication of SIR prior to			
2. Payment Enclosed:	Examiner action			
Check Credit card Money Other	113 1,840* 113 1,840* Requesting publication of SIR after Examiner action			
FEE CALCULATION	115 110 215 55 Extension for reply within first month			
1. BASIC FILING FEE	116 390 216 195 Extension for reply within second month			
Large Entity Small Entity	117 890 217 445 Extension for reply within third month			
Fee Fee Fee Fee Description Code (\$) Code (\$) Fee Paid	118 1,390 218 695 Extension for reply within fourth month			
101 710 201 355 Utility filing fee 710.	128 1,890 228 945 Extension for reply within fifth month			
106 320 206 160 Design filing fee	119 310 219 155 Notice of Appeal			
107 490 207 245 Plant filing fee	120 310 220 155 Filing a brief in support of an appeal			
108 710 208 355 Reissue filing fee	121 270 221 135 Request for oral hearing			
114 150 214 75 Provisional filing fee	138 1,510 138 1,510 Petition to institute a public use proceeding  140 110 240 55 Petition to revive - unavoidable			
SUBTOTAL (1) (\$) 710.00				
2. EXTRA CLAIM FEES	141 1,240 241 620 Petition to revive - unintentional  142 1,240 242 620 Utility issue fee (or reissue)			
Fee from	142 440 042 200 Pasier issue for			
Extra Claims below Fee Paid  Total Claims $25 - 20^{++} = 5 \times 18 = 90$ .	144 600 244 300 Plant issue fee			
Independent Claims 16 - 3** = 13 x 80 = 1040	122 130 122 130 Petitions to the Commissioner			
Multiple Dependent =	123 50 123 50 Petitions related to provisional applications			
	126 240 126 240 Submission of Information Disclosure Stmt			
Large Entity Small Entity Fee Fee Fee Fee Description Code (\$) Code (\$)	581 40 581 40 Recording each patent assignment per property (times number of properties)			
Code (\$) Code (\$) 103 18 203 9 Claims in excess of 20	146 710 246 355 Filing a submission after final rejection			
102 80 202 40 Independent claims in excess of 3	(37 CFR § 1.129(a))			
104 270 204 135 Multiple dependent claim, if not paid	149 710 249 355 For each additional invention to be examined (37 CFR § 1.129(b))			
109 80 209 40 ** Reissue independent claims over original patent	179 710 279 355 Request for Continued Examination (RCE)			
110 18 210 9 ** Reissue claims in excess of 20 and over original patent	169 900 169 900 Request for expedited examination of a design application			
SUBTOTAL (2) (\$)1130.00				
*Reduced by Basic Filing Fee Paid SUBTOTAL (3) (\$)				
SUBMITTED BY Complete (if applicable)				
Name (Print/Type) Kurt C. Olsen	Registration No. (Attorney/Agent) 29,961 Telephone 925–294–3573			
Signature /	Date 10/24/00			

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

# MOBILE MONOLITHIC POLYMER ELEMENTS FOR FLOW CONTROL IN MICROFLUIDIC DEVICES

**Inventors:** 

Ernest F. Hasselbrink, Jr.

Jason E. Rehm

Timothy J. Shepodd

#### Certificate of Mailing Under 37 CFT § 1.10

I hereby certify that this New Application Transmittal and documents referred to as enclosed therein are being deposited with the United States Postal Service on October 24, 2000 in an envelope as "Express Mail Post Office to Addressee" Mailing Label Number EL177882857US addressed to: Assistant Commissioner of Patents, Box Patent Application, Washington, DC 20231.

Date of Deposit:

Person Making Deposit:

Attorney Docket No. SD- 8298

Signature:

For Applicant: Hasselbrink, et al.

Express Mail Mailing Label No. EL177882857US

5

## MOBILE MONOLITHIC POLYMER ELEMENTS FOR FLOW CONTROL IN MICROFLUIDIC DEVICES

#### CROSS-REFERENCE TO RELATED APPLICATIONS

Not applicable.

#### STATEMENT OF GOVERNMENT INTEREST

This invention was made with Government support under contract no.

DE - AC04 - 94AL85000 awarded by the U. S. Department of Energy to

Sandia Corporation. The Government has certain rights in the invention.

#### BACKGROUND OF THE INVENTION

The invention is directed generally to improved apparatus for controlling and regulating the flow of fluids in microfluidic systems and particularly to devices that control and regulate fluid flow in microfluidic systems by means of a mobile, monolithic polymer element. The invention further includes methods for the manufacture of these monolithic polymer elements that provides for the polymer element to be cast-in-place in such a manner that the element will conform to the shape of the microchannel walls and not bond to the microchannel walls, thereby retaining mobility.

Recent advances in miniaturization have led to the development of microfluidic systems that are designed, in part, to perform a multitude of chemical and physical processes on a micro-scale. Typical applications include analytical and medical instrumentation, industrial process control equipment, and liquid and gas phase chromatography. In this context, there is

5

a need for devices that have fast response times to provide very precise control over small flows as well as small volumes of fluid (liquid or gas) in microscale channels. In order to provide these advantages, it is necessary that the flow control devices be integrated into the microfluidic systems themselves. The term "microfluidic" refers to a system or device having channels or chambers that are generally fabricated on the micron or submicron scale, i.e., having at least one cross-sectional dimension in the range from about 0.1 µm to about 500 µm. Examples of methods of fabricating such microfluidic systems can be found in U.S. Patent No. 5,194,133 to Clark et al., U.S. Patent No. 5,132,012 to Miura et al., U.S. Patent No. 4,908,112 to Pace, U.S. Patent No. 5,571,410 to Swedberg et al., and U.S. Patent No. 5,824,204 to Jerman.

Although there are numerous micro-fabricated valve designs that use a wide variety of actuation mechanisms (Shoji and Esashi, J. Micromech.

Microeng., 4, 157-171, 1994), most dissipate relatively large amounts of power to the chip or substrate or require complex assembly which limits their use in practical systems. Most microvalves are manufactured from silicon and are therefore not easily integrated into non-silicon microchip platforms such as silica, glass, or synthetic materials such as organic polymers. A microvalve using an electromagnetic drive is described in U.S. Patent No. 5,924,674 issued to Hahn et al. July 20, 1999. Microvalves using thermopneumatic expansion as the actuation mechanism and a shape memory

5

alloy diaphragm and bias spring are commercially available. However, these microvalves suffer from the fact that they consume relatively large amounts of power during operation, typically between 200 and 1500 mW depending upon the design. This high power consumption can be a significant disadvantage when heating of the fluid must be avoided, when batteries must supply power, or when the microvalve is placed on a microchip. Moreover, valves using the aforementioned actuation mechanisms can only generate modest actuation pressures. Perhaps most importantly, these valve designs can be difficult and costly to manufacture and assemble, frequently requiring assembly in a clean room environment.

Recognizing that the power requirements of conventional valves limited their use in practical systems, Beebe et al. (*Nature*, 404, 588-590, April 2000) describe a flow control system consisting of a hydrogel. The hydrogel valves provide local flow control by expanding or contracting when exposed to various pH levels. While eliminating the need for associated power supplies, these valves suffer from slow response times ( $\approx$ 8-10 sec) and are able to withstand only modest pressure differentials.

Unger et al. (Science, 288, 113-116, April 2000) describe an arrangement for controlling fluid flow in microchannels. Flow control is accomplished by the use of soft elastomer "control lines" that intersect the microfluidic channels fabricated in an elastomeric substrate material.

Applying pressure to the external surfaces of the control lines causes them to

10

ķŵ

f. 

**15**.

20

For: Hasselbrink

deform closing off that part of the channel they intersect. While eliminating the problem of power dissipation to the substrate, these valves require a microchannel having a specially shaped cross-section to seal properly. They also intrinsically require that pressure greater than in the channel be applied to the control line to keep the valve shut.

Ramsey in U.S. Patent No. 5,858,195 provides for valveless microchip flow control by simultaneously applying a controlled electrical potential to an arrangement of intersecting reservoirs. The volume of material transported from one reservoir to another through an intersection is selectively controlled by the electric field in each intersecting channel. In addition to the need for elaborate switching and control of electrical potential, there are problems with leakage of fluid from one channel to another through the common intersection because there is no mechanical barrier to diffusion. Further, this flow control method has essentially no control over pressure-driven flow. For example, the flow control of a 10 mM aqueous buffer at pH 7, using a 1000V/cm electric field in round channels about 50 µm in diameter, can be completely disrupted by a pressure gradient of only 0.1 psi/cm. Higher electric fields are generally prohibited because of rapid ohmic heating of the fluid. Furthermore, the presence of pH or conductivity gradients within the fluid can disrupt this valving scheme (Schultz-Lockyear et al., Electrophoresis, 20, 529-538, 1999).

SUMMARY OF THE INVENTION

5

Accordingly, the present invention is directed to a cast-in-place mobile monolithic polymer element or member and method of manufacture thereof, and devices for controlling and regulating fluid flow, including ionic current flow, that incorporate the novel mobile monolithic polymer element.

A microfluid control device, or microvalve can be made that comprises generally a cast-in-place, mobile monolithic polymer element, disposed within a microchannel, and driven by a displacing force that can be fluid (either liquid or gas) pressure or an electric field against a sealing surface, or retaining means that can be a constriction or a stop in the microchannel, to provide for control of fluid flow. As a means for controlling fluid flow, these devices possess the additional advantage that they can be used to effect pressure and electric field driven flows, eliminate or enhance diffusive or convective mixing, inject fixed quantities of fluid, and selectively divert flow from one channel to various other channels. They can also be used to isolate electric fields, and, as a consequence, locally isolate electroosmotic or electrophoretic flows.

The mobile monolith polymer element of the invention is not restricted to any particular shape or geometry except by the configuration of microchannel in which it functions and the requirement that it provide an effective seal against fluid flow for valving applications.

By providing a method for producing a monolithic polymer element that does not bond to surrounding structures, these polymer elements are free to

The first time first first of the state of t

20

5

move within the confines of a microchannel and can be translated within the microchannel by applying a displacing force, such as fluid pressure or an electric field to the polymer element. It is well known in the art, that if a mobile body within a microchannel has a surface charge density that is different from that of the walls of the microchannel, the body can be translated in the microchannel by the application of an electric field. Hence, translation of the polymer element can be achieved by application of electric fields.

By means of the invention, it is now possible to manufacture a family of fluid flow control, regulation, and distribution devices such as, but not limited to, microvalves, nano- and pico-liter pipettes and syringes needle valves, diverter valves, and water wheel flowmeters.

In contrast to the prior art, the microfluid control devices, or microvalves, disclosed herein can seal against pressures greater than 5000 psi, dissipate no heat to a substrate, and have a response time on the order of milliseconds. Calculations show that a monolithic polymer element 50  $\mu$ m in diameter and 200  $\mu$ m long, with a 0.1  $\mu$ m gap between the element and the wall has an actuation time (for a pressure differential across the element of about 1 psi) of about 1.1 msec.

The polymer element of the microfluid control devices can be made by a one-step lithography process employing a polymer material that is polymerized by radiation, such as by thermal, visible, or UV radiation.

5

Aftorney Docket: SD-8298 For: Hasselbrink

Electrostatic attraction between microchannel walls and the polymer element that could influence the mobility of the polymer element is of particular concern. However, by providing for the polymer and microchannel surfaces to have the same, or no, electric charge it has been found that the monolithic polymer element will not bond with or be attracted to the microchannel wall. Thus, the element can be moved back and forth freely within the microchannel by application of pressure to either end of the element, i.e., by developing a pressure differential across the polymer element. The profile of the polymer element can be further configured by the directed application of radiation, preferably from a laser, to selected regions of the actuator causing the polymer in the irradiated regions to depolymerize. This can include, by way of example, making the middle part of the actuator narrower than the ends or vice versa. Because the monolithic polymer element can be manufactured in-place within minutes the microfluid control devices that employ them do not require expensive and complicated manufacturing and/or assembly processes.

#### BRIEF DESCRIPTION OF THE DRAWINGS

The accompanying drawings, which are incorporated in and form part of the specification, illustrate the present invention and, together with the description, explain the invention. In the drawings like elements are referred to by like numbers.

Figure 1 is an embodiment of the invention illustrating its general

5

principle and operation.

Figure 2 illustrates a fixed volume syringe.

Figures 3a and 3b illustrate a shut-off valve configuration.

Figures 4a and 4b illustrate the operation of a two-way valve configuration.

Figures 5a and 5b are micrographs that show the sealing action of a cast-in-place variable area polymer element in a microchannel.

Figure 6 illustrates a method for manufacture of a polymer element in a microchannel.

Figure 7 shows a mechanical actuator embodiment.

Figure 8 is a schematic illustration of a method of selective depolymerization.

Figure 9 shows a diverter valve configuration produced by laser depolymerization of a cast-in-place polymer element.

Figure 10 illustrates a flowmeter.

#### DETAILED DESCRIPTION OF THE INVENTION

The present invention comprises a mobile monolithic polymer element that can be cast-in-place in a microchannel to control fluid and ionic current flow. The mobile monolithic polymer element of the invention is not restricted to any particular shape or geometry except by the configuration of the microchannel in which it functions and the requirement that it provide an effective seal against fluid flow at pressure up to about 5000 psi. The

5

invention further includes a method for the manufacture of these monolithic polymer elements that provide for the polymer element not only to be cast-in-place but also is such that the element will not chemically bond or be electrostatically attracted to the microchannel walls, thereby retaining mobility in the microchannel. Thus, the polymer elements are free to move within the confines of a microchannel and can be driven back and forth within the microchannel by appropriate application of a displacing force, pressure or an electric field. Consequently, the invention provides for incorporating a valve into a unitary structure that can be created *in-situ* on a substrate or microchip for controlling fluid flows in microchannels, wherein the fluid can be either liquid or gas.

Throughout the written description of the invention the terms channel and microchannel will be used interchangeably. Furthermore, the term "microfluidic" refers to a system or device having channels or chambers that are generally fabricated on the micron or submicron scale, e.g., having at least one cross-sectional dimension in the range from about 0.1  $\mu$ m to about 500  $\mu$ m, i.e., microchannels. The term fluid can refer to either a liquid or gas, the meaning being generally apparent from the context.

While the structure and function of the invention will be described and illustrated in relation to the microchannels and arrangements thereof it is understood that the microchannels themselves are part of a microfluidic device. The microfluidic device can be comprised of channels, reservoirs,

5

and arbitrarily shaped cavities that are fabricated using any of a number of art recognized microfabrication methods, including injection molding, hot embossing, wet or dry etching, or deposition over a sacrificial layer. The microfluidic device can also include holes and/or ports and/or connectors to adapt the microfluidic channels and reservoirs to external fluid handling devices.

Fig. 1 illustrates and embodies the principle and operation of the present invention, using the inventive mobile monolithic polymer element for controlling fluid flow. Device 100 is a check valve embodiment and comprises a mobile polymer element 120 disposed within a microchannel 130, provided with first and second inlets and retaining means 140 and 141. The monolithic polymer element is fabricated within the microchannel and thus conforms to the shape of the microchannel. Fluid pressure, applied by pressure means such as an HPLC pump or an electrokinetic pump (such as described in U.S, Patent Nos. 6,013,164 and 6,019,882 to Paul and Rakestraw) to either end of element 120 causes it to move one direction or the other in response to the applied pressure. When pressure is applied to the first, or right, inlet of microchannel 130, element 120 is moved to the left whereupon it seats against retaining means 141, allowing fluid to flow around it through bypass duct 131. However, when pressure is applied to the second, or left inlet, of microchannel 130, element 120 is moved to the right, where it

**Attorney Docket: SD-8298** 

THE REPORT OF THE PERSON OF TH

15

20

5

seats against retaining means 140, and fluid flow is restricted or stopped.

Fig. 2 illustrates another embodiment of the invention, a fixed volume injector or syringe 200. Two spaced apart retaining means 140 and 141 are fixed in microchannel 130 and the distance between them defines a fixed volume. A mobile polymer element or piston 120 is disposed in the microchannel and between the retaining means. By immersing one end of microchannel 130 into a liquid and applying a vacuum to the opposite end of the microchannel, or pressurizing the liquid, a volume of liquid can be drawn up onto the channel; the volume of liquid being determined by the distance between retaining means 140 and 141, minus the length of piston 120. By reversing the displacing force, the volume of liquid can be ejected. The check valve embodiment 100 and the fixed volume injector 200 can be combined to form a fixed volume pipette capable of sampling a fixed volume of fluid from one channel and depositing it into another.

Another embodiment of the invention, a shut-off valve 300, is illustrated in Figs. 3a and 3b. Microchannel 130 is intersected by a second microchannel 131. Microchannel 131 has a mobile polymer plug 120 disposed therein. In the open position (Fig. 3a) polymer plug 120 is drawn up into microchannel 131 and against retaining means 140. Applying gas or liquid pressure to microchannel 131 forces polymer plug 120 into the channel intersection (Fig. 3b) against retaining means 141 stopping fluid flow or ionic

For: Hasselbrink

current flow through microchannel 130.

5

the set that it made after the set of the se

. M

Hart and H with the upe H

15

20

A further embodiment, a two-way valve 400, is illustrated in Figs. 4a and 4b. Microchannels 131 and 132 provide for fluid inlet to a common intersection 130, having retaining means 141 and 142 disposed at each end of the intersection, and a polymer plug 120 disposed therein. Outlet microchannel 133 intersects common intersection 130 between the two retaining means 140 and 141. The device prevents pressure-driven flow from one inlet microchannel from entering the other inlet microchannel. By way of example, application of fluid pressure to microchannel 132 causes element 120 to be driven towards channel 131 where it is seated against retaining means 141 blocking flow into channel 131 (Fig. 4b). In this way, fluid can flow from one inlet channel without causing contamination of, or flow into, the other inlet channel. Multiple channel valves can be constructed by connecting multiple two-channel valves, such as valve 400, in series. By way of example, the outlet channel 133 can be connected to either of inlet channels 131 or 132 of a second two-channel valve, along with a third inlet channel. The application of pressure to any one of the three inlet channels can result in flow of only the pressurized fluid with little or no contamination of the other two input fluids.

In microfluidic systems generally it can be desirable to amplify flow rates or forces, particularly for mechanical linear actuation. This can be

20

5

accomplished, as illustrated in Figs. 5a and 5b, by means of a change in the cross-sectional area of the mobile monolithic element. A monolithic mobile plug 120 is fabricated in microchannel 130 (150 μm wide and 20 μm deep). As before, a pressurized fluid in contact with the left end of mobile plug 120 causes plug 120 to move to the right. This results in a lower rate of fluid flow in microchannel 131 (50 μm wide and 20 μm deep), but a higher pressure is developed in channel 131. Conversely, if pressurized flow forces mobile plug 120 to the left, away from microchannel 131, a higher flow rate, but lower pressure, is developed in microchannel 130.

Operation of the novel microchannel flow control devices disclosed above is dependent upon the ability to produce a monolithic polymer material that conforms to the shape of the microchannel, does not bond to surrounding structures, such as the microchannel walls, and can be polymerized by exposure to radiation, such as thermal radiation or visible or UV light. For purposes of describing the invention, the term "bond" will include electrostatic attraction as well as chemical bonding. Sources of such radiation include UV or visible lamps and lasers. Depending on the application, it can be desirable that the polymer monolith be either porous or nonporous; a property of the polymer generally defined by its formulation. The term "nonporous" means the absence of any porosity in the monolithic polymer element that would permit fluid under pressure, or otherwise, to pass

5

through the polymer element. Thus, in most cases, any open porosity that might be present has a pore diameter less than 5 nm. The term "porous" means that a pressure differential across the element results in some fluid flow through it. In general, this means pores larger than about 20 nm. A meso-porous porosity range also exists between these two porosity ranges wherein ionic current can flow through the polymer element but bulk fluid flow is negligible.

There are three basic requirements that must be fulfilled for successful fabrication of a mobile monolithic polymer element within a microchannel: 1) the monomer mixture must flow readily within the microchannel; 2) polymerization is initiated by exposure to radiation; and 3) the polymerized mixture must not bond to the channel wall.

The first requirement can be fulfilled by the choice of solvent. The solvent not only acts to help mobilize the monomer mixture but also acts as a diluent controlling the rate of polymerization of the monomer and causing polymerization not to extend substantially beyond the boundary of the radiation used to initiate polymerization. The second requirement is aided by the addition of a UV or visible light polymerization compound, such as 2,2'-azobisisobutyronitrile, to the mixture. The third requirement can be achieved by two means. The first, by using a polymer having a surface charge of the same sign as that on the surface of the microchannel. By way of example, glass has exposed SiO-groups at a pH of 2 or greater. Thus, in order that a

5

polymer material polymerized within a glass microchannel not bond to the glass surface, it too must have a negative surface charge.

Equivalence of surface charge of the polymer phase with that of the surrounding walls can be achieved by 1) adding suitable bifunctional monomers to the organic phase of the mixture to provide a charged polymer structure, or 2) by modifying the surface charge on a region of the microchannel wall by methods such as those described in U.S. Patent No. 6,056,860 issued to Goretty et al. May 2, 2000.

Bonding of the polymer to the microchannel walls can also be achieved by making the microchannel generally non-reactive by treating the microchannel as disclosed by Goretty et al., or by fabricating the microchannels on a non-reactive substrate, such as Teflon®, that does not bond with the formulations described herein.

The requirements set forth above are met by the general class of monomer and solvents described below which form part of this invention. The monomer mixtures are designed to form a single phase mixture at temperatures below about 40 °C and generally comprise four components:

1. A cross-linking agent selected from the group ethylene glycol diacrylate, diethylene glycol diacrylate, propylene glycol diacrylate, butanediol diacrylate, neopentyl glycol diacrylate, hexanediol diacrylate, pentaerythritol triacrylate, pentaerythritol tetracrylate, trimethylolpropane triacrylate, or divinyl benzene, and mixtures thereof. The cross-linking agent

**Attorney Docket: SD-8298** 

TO BUT THE 10 mai that alla that

H H HIIII ALM Str.

1

153

20

5

generally present in about 10-50 vol% of the monomer mixture.

- 2. Tetrahydrofurfuryl acrylate (0-60 vol% of the monomer mixture).
- 3. A nonpolar monomer selected from the group branched or straight chain  $C_1$ - $C_{12}$  alkyl acrylates, styrene, or mixtures thereof (10-60 vol% of the monomer mixture).
  - 4. A monomer selected to carry a charge at some range of pH values between about 2 and 12. Monomers can include C<sub>1</sub>-C<sub>12</sub> alkyl or aryl acrylates substituted with sulfonate, phosphate, boronate, carboxylate, amine, or ammonium, or acrylamido analogs of the acryoyloxy compounds above, or mixtures of the above (0.1 to 5 vol\% of the monomer mixture).

The solvent system can comprise:

- 1. Water (5-40 vol%) containing 5-100 mM buffer salts.
- 2. Other solvents selected from C<sub>1</sub>-C<sub>6</sub> alcohols, C<sub>4</sub>-C<sub>8</sub> ethers, C<sub>3</sub>- $C_6$  esters,  $C_1$ - $C_4$  carboxylic acids, methyl sulfoxide, sulfolane, or N-methyl pyrrolidone, and mixtures thereof (60-95 vol%).

The monomer to solvent ratio (by vol%) can vary from about 90:10 to 30:70 with a ratio of 60:40 preferred.

The following example illustrates generally a method for preparing mobile monolithic polymer materials in capillaries and microchannels, in accordance with the present invention. This example only serves to illustrate the invention and is not intended to be limiting. Modifications and variations

may become apparent to those skilled in the art, however these modifications and variations come within the scope of the appended claims. Only the scope and content of the claims limit the invention.

#### **EXAMPLE**

A monomer mixture was prepared by mixing together the following constituents:

40 ml 1,3-butanedioldiacrylate (BDDA)

39 ml tetrahydrofurfuryl alcohol (THFA)

20 ml of hexyl acrylate

0.8 ml acryloyloxyethyltrimethylammonium methyl sulfate
An amount of photo-initiator (such as 2,2'-azobisisobutyronitrile) equal to
0.5% of the weight of the monomer mixture was added to the monomer
mixture.

A solvent was prepared by mixing together:

45 ml acetonitrile

40 ml 2-methoxyethanol

15 ml of 5 mM phosphate buffer (pH 8)

The monomer and solvent were mixed together in a ratio (by vol%) of 60:40 and the mixture was filtered and degassed.

Referring now to Fig. 6, a mask 650 defining the outline of the polymer monolith to be produced was applied to the surface of a silica capillary tube arrangement comprising a silica capillary 131, about 50 µm wide, and silica

5

capillary 130, about 100 µm wide, joined together on a common axis (Fig. 6), the combination having zero dead volume at the intersection. The liquid mixture was loaded into the capillaries and polymerized by exposure to a UV lamp (0.2 W/cm<sup>2</sup>), through mask 150, for about 4 minutes to form the solid polymer element 120 shown in Fig. 6. The polymer element shown in Fig. 6 was very similar in appearance to that of Fig. 5, except that the element did not extend into the smaller diameter channel. The polymerization time can vary depending upon the intensity and wavelength of the radiation source. Polymer elements have been fabricated in this manner using light having wavelengths of about 257 nm, 355 nm, and 405 nm. It is preferred that unreacted monomer be removed by flushing the capillary with a solvent such as acetonitrile. It was found that element 120 moved freely back and forth within microchannel 130 under applied pressure from either end of the microchannel until element 120 was seated against capillary 131. The end of capillary tube 130, distal from the joint, was attached to an HPLC pump to apply pressure to mobile polymer element 120. After polymer element 120 was seated against capillary 131 pressures greater than 5000 psi could be applied with no leakage of fluid across the interface between capillaries 130 and 131. However, when pressure was relieved the polymer element could be freely moved away from the capillary interface ("unseated"). Furthermore, it was found to be possible, by controlling the pressure applied to capillary 131,

5

to extend polymer element 120 out of capillary 130 and then retract it back into the capillary.

Using the fabrication method set forth above, the inventors have shown that it is possible to make mobile polymer monoliths in-situ in channels ranging from 20 to 150 µm in diameter. Moreover, using the method described above there is, in principle, no reason why mobile monolithic polymer elements as small a few microns and as large as 1000 µm in diameter cannot be made.

The embodiment illustrated in Figs. 5a and 6 can be modified to provide a mechanical actuating function, as illustrated in Fig. 7. Here, an actuator of conventional design consisting of a monolithic mobile element 120 and actuating rod 510 is disposed in a microchannel arrangement, such as shown. Application of an alternating pressure to the end of element 120 opposite the actuating rod causes actuating rod 510 to periodically engage the object 520 being mechanically actuated, such as a membrane, wheel, rocker, lever, pin, or valve.

The polymer composition, prepared as above, possesses the additional advantage in that it can be depolymerized by energetic radiation (thermal or UV). By way of example, the selective application of 257 nm light from a frequency doubled Argon-ion laser to various parts of a polymer monolith, prepared by the method above, can cause depolymerization of the polymer in those areas exposed to the radiation, as shown in Fig. 8a, a side view of a

5

microchannel and the polymer monolith contained therein. During the step of selective depolymerization, it can be desirable to periodically or continuously flush the illuminated region of the polymer monolith, to prevent depolymerized material, or its decomposition products, from clogging the microchannel. Video pictures of the depolymerization step have shown that monolithic elements depolymerize slowly from that part of the monolith upon which the light is incident; it is believed that this is because the polymer strongly absorbs mid- to deep-UV light within a distance of a few microns from the surface. Hence, by ending the exposure before the entire depth of the monolith is depolymerized, a gap 821 may be lithographically patterned between the top of the microchannel and the polymer monolith itself, as shown in Fig. 8b. In this way, it is now possible to make three-dimensional structures that cannot be produced by conventional lithographic polymerization, and would be impossible to machine conventionally. The dimensions of the area to be depolymerized are delineated by a mask and/or focusing of a laser, and the depth of the removed region is determined by the intensity of the incident light and the duration of exposure. Since the microchannel formed by traditional micromachining techniques (wet or dry etching) are not cylindrical, the cast-in-place polymer monolith is naturally constrained from rotating, unless there is extensive depolymerization along the entire length of the monolith.

Fig. 9 shows a plan view of a diverter or 2-way valve structure

20

5

manufactured using the selective depolymerization method set forth above. The mobile monolithic element 120 has a depolymerized gap 821 along its top (as shown in Fig. 8b), formed near its center for diverting fluid from one microchannel into either of two separate microchannels. Microchannel 131 provides a common intersection for microchannels 130, 132, and 133.

Application of pressure to microchannel 131 causes polymer element 120 to be drawn to one side blocking fluid flow from microchannel 130 into one of the parallel opposing microchannels (132 or 133). Application of pressure to the other side of element 120 causes fluid flow to be blocked to the other microchannel. This device has the property that, the pressures within microchannels 130, 132, and 133 impose no differential pressure across the length of element 120. Hence element 120 can be actuated by pressures much lower than the pressure in the controlled microchannels 130, 132, and 133.

The invention is not limited to plug-shaped geometries for the polymer element. Fig. 10 illustrates an embodiment of the invention as a rotational flowmeter. Here, microchannel 910, having an inlet and outlet segment, intersects a cavity 920, which separates the inlet and outlet segments of microchannel 910. The cavity is micromachined so as to leave a central hub 940. A rotatable polymer disc 930, having a plurality of projections 935 distributed around its circumference, is disposed in cavity 920 and on hub 940 around which it rotates. The projections can be uniformly distributed

Attorney Docket: SD-8298

20

5

around the circumference and the space between the projections defines a fixed volume. Thus, each partial rotation of polymer disc 930 injects a fixed volume of fluid, delivered by the inlet segment of microchannel 910, into the outlet segment of the microchannel. Detection of the movement of the polymer disc can be achieved by a wide range of optical techniques. By way of example, a weak but focused light can be projected into the path of polymeric projections 935. Each time a polymer projection moves onto the light beam a portion of the light will be absorbed and the decrease in intensity of the light beam can be detected.

In summary, the present invention is directed to a cast-in-place mobile, monolithic polymer element for controlling fluid and ionic current flow in microchannel systems and method of manufacture thereof. Fluid flow control devices for microfluidic applications, and microvalves can be made incorporating the cast-in-place, mobile monolithic polymer element of the invention, disposed within a microchannel, and driven by a displacing force that can be an electric field or fluid or gas pressure against a sealing surface to provide for control of fluid flow. As a means for controlling fluid flow, these devices possess the additional advantage that they can be used translationally and/or rotationally to effect pressure driven, electroosmotic, or electrophoretic flow, to eliminate or enhance diffusive or convective mixing, to inject fixed quantities of fluid, and to selectively divert flow from one channel to various other channels. The polymer elements are made by the

Attorney Docket: SD-8298 For: Hasselbrink

application of lithographic methods to monomer mixtures formulated in such a way that the resulting polymer element will not bond to microchannel walls. These polymer elements can seal against pressures greater than 5000 psi, and have a response time on the order of milliseconds. Finally, by the use of energetic radiation it is possible to depolymerize selected regions of the polymer element to form shapes that cannot be produced by conventional lithographic patterning and would be impossible to machine.

#### For: Hasselbrink

#### **CLAIMS**

We claim:

5

10 Ham der

W. C.B.

Į.

20

1. A device for controlling fluid flow in a microchannel, comprising:

a mobile, monolithic polymer element disposed in the microchannel, wherein said mobile, monolithic polymer element is made by polymerizing a monomer mixture within the microchannel; and

means for providing a displacing force to control the movement of said polymer element in the microchannel.

- 2. The device of claim 1, wherein the displacing force is pressure or voltage.
- 3. The device of claim 1, further including spaced apart retaining means disposed within the microchannel.
- 4. The device of claim 3, wherein said retaining means comprises a sealing surface.
- 5. A method for making a mobile, monolithic polymer element in a microchannel, comprising;
- a) injecting a monomer mixture dissolved in a solvent into the microchannel, wherein the composition of the monomer mixture is such that the polymer formed by polymerizing the monomer does not bond to the microchannel wall;
  - b) polymerizing the monomer by application of radiation; and
  - c) flushing unpolymerized monomer mixture from the microchannel.
- 6. The method of claim 5, wherein the radiation is UV, visible, or thermal radiation.

5

7. A method for making a monolithic polymer element in a microchannel such that the polymer element conforms to the configuration of the microchannel and does not bond to the microchannel wall, comprising the steps of:

preparing a monomer mixture by mixing together

- a) one or more cross-linking agents selected from the group including ethylene glycol diacrylate, diethylene glycol diacrylate, propylene glycol diacrylate, butanediol diacrylate, neopentyl glycol diacrylate, hexanediol diacrylate, pentaerythritol triacrylate, pentaerythritol tetracrylate, trimethylolpropane triacrylate, or divinyl benzene,
  - b) tetrahydrofurfuryl acrylate,
- c) at least one nonpolar monomer selected from the group branched or straight chain  $C_1$ - $C_{12}$  alkyl acrylates, or styrene, and
- d) at least one monomer capable of carrying a charge at a pH of between about 2 and 12 selected from the group including  $C_1$ - $C_{12}$  alkyl or aryl acrylates substituted with sulfonate, phosphate, boronate, carboxylate, amine, or ammonium;

adding the monomer mixture to a solvent, comprising;

- a) water containing up to 100 mM buffer salts, and
- b) at least one of the group including  $C_1$ - $C_6$  alcohols,  $C_4$ - $C_8$  ethers,  $C_3$ - $C_6$  esters,  $C_1$ - $C_4$  esters,  $C_1$ - $C_4$  carboxylic acids, methyl sulfoxide, sulfolane, or N-methyl pyrrolidone, and

a polymerization initiator, wherein the monomer/solvent mixture forms a single phase mixture at a temperature below about 40 °C;

Hade group generalized from the state of the

15 mm m mm n

loading the combined mixture into a capillary tube;

applying a mask to the surface of the capillary tube, wherein the mask defines the shape of the polymer monolith to be produced;

polymerizing the combined mixture by exposing the monomer mixture to radiation through the mask; and

flushing unpolymerized monomer from the microchannel.

- 8. The method of claim 7, wherein the radiation includes thermal, visible, or UV radiation.
- 9. The method of claim 8, wherein wavelength of the radiation is greater than about 257 nm.
- 10. A mobile polymer monolith disposed in a microchannel and made by the method of claim 7.
- 11. A device for controlling fluid flow in a microchannel, comprising a mobile monolithic polymer element disposed in the microchannel, wherein said polymer element is made by the method of claim 7; at least one retaining means disposed in the microchannel; and means for applying a displacing force to the either end of the microchannel.
- 12. A device for increasing fluid flow rates in a capillary, comprising:
- a first and a second capillary joined together coaxially, wherein said first capillary has a larger diameter than said second capillary; and a mobile monolithic polymer element disposed in said first capillary.
  - 13. A device for amplifying fluid forces in a capillary, comprising:

    a first and a second capillary joined together coaxially, wherein said
- 25 first capillary has a larger diameter than said second capillary; and

25

a mobile monolithic polymer element disposed in said first capillary, wherein said polymer element consists of a first and second coaxial segments, and wherein the second segment has a diameter adapted to fit within the second capillary.

5 14. A rotational flowmeter, comprising:

a microchannel system disposed on a substrate, the microchannel system comprising a microchannel intersecting a cavity, wherein the cavity divides the intersecting microchannel into an inlet channel and an outlet channel; and

a rotatable polymer disc disposed on a hub within the cavity, wherein said rotatable polymer disc has projections distributed around its circumference such that rotation of polymer disc delivers a fixed volume of fluid from the inlet channel to the outlet channel.

- 15. The flowmeter of claim 14, further including means for detecting the rotation of said polymer disc.
- 16. A device for controlling fluid flow in microchannels, comprising:
- a first and a second intersecting microchannels, wherein said first microchannel includes two spaced apart retaining means;

a mobile monolithic polymer element disposed in said first microchannel and moveable between the retaining means to block fluid flow through said second microchannel; and

means for providing a displacing force to control the movement of said polymer element.

17. A device for controlling fluid flow in microchannels, comprising:

a plurality of microchannels converging at a common intersection,

25

wherein at least one of said plurality is a fluid inlet, and wherein the common intersection includes spaced apart retaining means and a mobile polymer monolith moveable between the retaining means to block fluid flow into one or more of said plurality of microchannels.

5 18. A method for shaping a monolithic polymer element disposed within a microchannel, comprising:

exposing the surface of the polymer element to energetic radiation to remove a portion of the surface and thereby shape the polymer element; and

flushing the microchannel with a liquid to remove depolymerized material.

- 19. The method of claim 18, wherein the source of energetic radiation is a laser.
- 20. The method of claim 19, wherein the laser is a frequency doubled Argonion laser operating at 257 nm.
- 21. A valve for controlling fluid flow in microchannels, comprising:
- a plurality of microchannels in fluid communication with a central microchannel, wherein at least one of said plurality is a fluid inlet, and wherein the central microchannel includes spaced retaining means and a mobile polymer monolith moveable between the retaining means, wherein the polymer monolith, shaped by the method of claim 16, provides for diverting fluid from the fluid inlet and into one or more of the plurality of microchannels.
- 22. A method of making a mobile, monolith polymer element in a microchannel, comprising:
  - a) preparing a monomer mixture by mixing together 1,3-

butanedioldiacrylate, tetrahydrofurfuryl alcohol, hexyl alcohol, acryloyloxyethyltrimethylammonium methyl sulfate, and a photoinitiator;

- b) preparing a solvent mixture by mixing together acetonitrile, methoxyethanol, and phosphate buffer;
- c) mixing together the monomer and solvent mixtures in the ratio of 60:40 by volume;
  - d) loading the combined mixture into a capillary tube;
- e) polymerizing the combined mixture by exposure to UV radiation; and.
  - f) flushing unreacted monomer from the microchannel.
- 23. A mobile monolithic polymer element disposed within a microchannel and made by the method of claim 22.
- 24. A device for controlling fluid flow in a microchannel, comprising a mobile monolithic polymer element disposed in the microchannel, wherein said polymer element is made by the method of claim 22;

at least one retaining means disposed in the microchannel; and means for applying a displacing force to the either end of the microchannel.

25. A device for controlling ionic current flow in a microchannel, comprising:
a mobile, monolithic polymer element disposed in the microchannel,
wherein said mobile, monolithic polymer element is made by polymerizing a
monomer mixture within the microchannel; and

means for providing a displacing force to control the movement of said polymer element in the microchannel.

20

10

King July Rion was all hands in rather the princip in the state state of the state

#### For: Hasselbrink

#### **ABSTRACT**

A cast-in-place and lithographically shaped mobile, monolithic polymer element for fluid flow control in microfluidic devices and method of manufacture. Microfluid flow control devices, or microvalves that provide for control of fluid or ionic current flow can be made incorporating a cast-in-place, mobile monolithic polymer element, disposed within a microchannel, and driven by either fluid or gas pressure against a retaining or sealing surface. The polymer elements are made by the application of lithographic methods to monomer mixtures formulated in such a way that the polymer will not bond to microchannel walls. The polymer elements can seal against pressures greater than 5000 psi, and have a response time on the order of milliseconds. By the use of energetic radiation it is possible to depolymerize selected regions of the polymer element to form shapes that cannot be produced by conventional lithographic patterning and would be impossible to machine.








Fig. 1












. .



Liquid (left)/gas (right) interface barrier



F19.56






Fig. 7

1.5

FOCUSED UV CIGHT





Fig fa



. .




Fig. 9

